

PRODUCT DESCRIPTION

THE **THERMOTEC DHU75** IS A HOT MELT ADHESIVE OF PREMIUM QUALITY, PRESENTED IN CLEAR STICKS. IT OFFERS AN EXCELLENT ADHERENCE TO A WIDE VARIETIES OF MATERIALS. THIS ADHESIVE IS APPROVED FOR USE IN FOOD PROCESSING ESTABLISHMENTS PROVIDED THAT IT IS APPLIED TO THE OUTER SURFACE OF THE PACKAGING MATERIALS.

TECHNICAL DATA

TYPE :	ETHYL-VINYL ACETYL (EVA) CO-POLYMER
COLOUR :	TRANSPARENT AND COLORLESS
ODOUR :	SLIGHT RESIN ODOUR
APPERANCE :	STICKS
SOFT POINT :	82°C-92°C(180°F-198°F)
TOXICITY :	NO HAZARDOUS INGREDIENTS
VISCOSITY :	15000 CPS to 25000 CPS @ 177°C(350° F)
SPECIFIC GRAVITY:	-
MAXIMUM OPEN TIME :	75 SECONDS
SETTING TIME :	VARIABLE
WORKING TEMPERATURE :	160-200°C (320-392°F)
DIAMETER :	11,2MM (0,44")
COVERAGE :	NOT AVAILABLE
STORAGE :	STORE IN CLOSED CONTAINER IN A DRY PLACE. AVOID DIRECT CONTACT WITH THE HEAT AND LIGHT. USE THE OLDEST MATERIAL FIRST (FIFO). KEEP OUT OF CHILDREN REACH.

CARACTERISTICS

- EXCELLENT ADHESION TO PLASTICS, WOODS, CERAMICS, TEXTILES, LEATHERS, GLASS, PAPERS AND PAPERBOARDS
- STRONG ADHESION BUT STILL OFFERS A FLEXIBLE JOINT
- SUPERIOR HEAT RESISTANCE
- EXCELLENT FLOW

TYPICAL APPLICATION

THIS ADHESIVE IS RECOMMANDED FOR ASSEMBLY WORK, CARPENTRY, PACKAGING, ELECTRONICS AND REPAIRS.

IMPORTANT NOTICE

ALL STATEMENTS, RECOMMENDATIONS AND TECHNICAL INFORMATION CONTAINED IN THIS DOCUMENT ARE BASED ON TESTS AND INFORMATION WHICH TEC-N-TEC BELIEVES TO BE ACCURATE AS OF THIS DATE. THE BUYERS HOWEVER SHOULD TEST THIS PRODUCT BEFORE USE. TEC-N-TEC WILL ASSUME NO OBLIGATION OR LIABILITY FOR RESULTS OBTAINED FROM THE USE OF THIS PRODUCT.

THE PRODUCT AND INFORMATION HEREIN ARE BELIEVES TO BE TRUE. TEC-N-TEC INC. WILL NOT BE LIABLE FOR ANY DIRECT, INDIRECT CONSEQUENTIAL ECONOMIC OR ANY OTHER DAMAGE WHATSOEVER, EXCEPT TO REPLACE THE PRODUCT AND OR REFUND THE PURCHASE PRICE TO THE PURCHASER.

**TEC-N-TEC INC.**

8244 PASCAL-GAGNON
MONTREAL, QC H1P 1Y4

TEL : (888)832-7777 - (514)325-7777
FAX : (888)832-0282 - (514)325-0282

WEBSITE : WWW.TEC-N-TEC.COM
EMAIL : PRO@TEC-N-TEC.COM