

**PRODUCT DATA****Bostik® Thermogrip®  
6363****HOT MELT  
ADHESIVES****Product Description**

Bostik® Thermogrip® 6363 is a general purpose, medium open time hot melt which exhibits good bonding characteristics on wood, metal, paper, fabrics, leather, ceramics and plastics.

Bostik® 6363 is in compositional compliance with FDA regulation 21 CFR 175.105 for food packaging.

Bostik® 6363 has been approved for various automotive applications.

**Product Benefits**

- Medium open time means more assembly time
- Good bond to a wide range of materials
- Aggressive tack

**Product Applications**

- Furniture repair and assembly
- Leather products—reinforcement and repair
- Component staking PC boards
- Automotive assembly or repair

**Application Information**

1. All surfaces should be clean and free of contaminants. If necessary, clean surfaces with solvent.
2. Apply the adhesive to the more difficult-to-bond surface. In general, hard, smooth surfaces are more difficult to bond than rough, porous surfaces.

**Metals should be pre-warmed** up to 200°F (95°C) for optimum results.

3. Open-time varies depending on application temperature, amount of adhesive applied, type of substrate and ambient temperature conditions.
4. Mate the surfaces to be bonded as quickly as possible after adhesive has been applied for optimum bond strength.

(continued...)

**Application Information (...continued)**

5. Use firmest pressure practical for object being bonded. Do not move or adjust surfaces after contact has been made, as inferior bond strength will result.
6. Typically, a properly formed hot melt adhesive bond will achieve 50% of its strength after 1 minute, 75% after 1 hour, and 100% after 1 day.

**Typical Physical Properties\* (After 24 Hour Cure)**

Color:	Off White
Size (dia. x length):	1/2" x 4" 1/2" x 15"
Odor:	Slight
Softening Range:	167°F to 197°F (75°C to 92°C)
Specific Gravity:	0.98 gms/cc
Viscosity, cps: @350°F (177°C)	20,500
Open Time:	40 secs.
Temperature Resistance:	-20°F to 125°F (-29°C to 52°C)

**Bond Characteristics**

Bond Strength, Shear, psi :	
Plywood	565
Chemical Resistance:	
Water	Good
Acids & Alkalies	Fair
Fats & Oils	Poor
Solvents	Poor

**Storage and Handling**

Shelf Life:	999 days @ 73.4°F (23°C)
Shipping and storage:	Between 40°F to 95°F (4°C to 35°C)
Further Information:	Please refer to MSDS for complete details.

\* Values given are not intended to be used in specification preparation.

**IMPORTANT NOTICE**

All statements, technical information and recommendations set forth herein are based on tests which Bostik Findley, Inc. believes to be reliable. However, Bostik Findley, Inc. does not guarantee their accuracy or completeness. The buyer should conduct its own tests of this product before use to determine proper preparation technique and suitability for proposed application. Any sales of this product shall be on terms and conditions set forth on Bostik Findley, Inc.'s order acknowledgment. Bostik Findley, Inc. warrants that the product conforms with Bostik Findley, Inc. written specifications, and is free from defects. BOSTIK FINDLEY, INC. DISCLAIMS ALL OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING THE WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. THE BUYER'S SOLE REMEDY FOR NONCOMPLIANCE WITH THIS WARRANTY SHALL BE FOR THE REPLACEMENT OF THE PRODUCT OR REFUND OF THE BUYER'S PURCHASE PRICE. IN NO CASE WILL BOSTIK FINDLEY, INC. BE LIABLE FOR DIRECT, CONSEQUENTIAL ECONOMIC OR OTHER DAMAGES.

**Bostik Findley, Inc.**  
211 Boston Street  
Middleton, MA 01949-2128 USA  
Tel: 1-888-603-8558  
Fax: 978-750-7293  
www.bostikfindley-us.com

HM-6363-05/03